



U38 – MICRONEUCE – Base mortar

DESCRIPTION: MICRONEUCE – Base mortar, is based on special water-based

copolymers, loads, aggregates and special additives, which provide a good adhesion to the surface, good filling power and a good

flexibility.

It is used in the smoothing phase of the surface.

FEATURES: – Good filling capacity.

Good penetration capacity.Strong hardness once dry

- Good waterproofing and flexibility.

SPECIFICATIONS: - Density 1,500±0,10

Aspect.....Textured and milky.

- **VOC** (volatile organic compound)....^a) EU limit value set for this product cat. (A/g) 30 g/l (2010). This product contains a

maximum of 6 g/l VOC.

RECOMMENDED USE: MICRONEUCE - Base Mortar, in a mono-component coating

indicated as a surface preparation (of the base) to then coat with the MICRONEUCE SYSTEM, where there is a need to regularize the

surface or even increase its hardness and consistency.

It can be applied on floors and exterior and interior walls, over different types of surfaces, such as: cement, concrete, ceramic

coating, plaster, stone (mineral surfaces), wood.

SURFACE PREPARATION:

The surfaces have to be dry, hardened, cohesive, clean of dust or

other pollutants (oils, repellents, varnishes, grease, among others)

which affect the adhesion conditions.

To always verify the adhesion degree over stripped, painted surfaces, façades with ceramic coating, tiles, powdery plaster and concrete. In these cases, we advise to apply 1 coat of

IMPERNEUCE, mixed in equal parts with cement.

APPLICATION: Before to use mix energetically the product.

After analyzing and preparing the surface, to apply a layer of basic mortar with a stainless steel trowel. Let dry for 24 hours to apply

the MICRONEUCE SYSTEM.

DILUTION: This product is supplied ready to use.

NEUCE S.A., THE RIGHT IS RESERVED OF ALTERING ANY CONSTANT DATA IN THIS PUBLICATION WITHOUT NOTICE Edition n.º $1\ 2016-03-24$





COVERAGE: We advise an average performance of 600 gr/m² and per layer.

CLEAN-UP: With water, right after application.

USE

RECOMMENDATIONS Application temperature: 5°C to 30°C.

Do not apply with a rainy weather or a strong heat, strong winds, on

frozen or defrosting surfaces.

- Do not apply on surfaces that are friable or little resistant.

WARNING: "MICRONEUCE – Base mortar" doesn't present any risk for

health.

Keep out of the reach of children.

For more information, please read our product Safety Data Sheet.

STORAGE AND

PACKAGING: Packages should be kept properly closed, in good environmental

conditions of temperature and humidity, and spend the product on

the chronological order of supply.

Use it, with preference, up to 1 year after its manufactured date.

It is supplied in packages of 5 Kg and 25 Kg.

Note a) The value of the VOC previously mentioned concerns ready-to-use products, according to the technical specifications that we recommend. We do not take any responsibility for other mixtures made to the product. We draw special attention to all our agents for the responsibility that they take by not respecting what the Directive 2004/42/CE establishes.

NEUCE S.A., THE RIGHT IS RESERVED OF ALTERING ANY CONSTANT DATA IN THIS PUBLICATION WITHOUT NOTICE Edition $n.^{\circ}\,1$ 2016-03-24