

## 06.04 – TEXTURFLEX – Flexible Sand-finish Paint

### DESCRIPTION:



Based on an acrylic emulsion and pigments and resistant mineral charges, “TEXTURFLEX” is a textured paint, impermeable, flexible, appropriate for exterior walls coating. Provides a tinting of a wide range colors in the BIG MIX system.

### FEATURES:

- Easy to apply and excellent adhesion.
- Good resistance to bad weather.
- Impermeable to water but permeable to water vapor.
- Great flexibility.
- Good covering, allowing the disguise of the surface irregularities

### SPECIFICATIONS:

- **Density**.....1,350 ± 0,10 (p/ white color)
- **Viscosity**..... 250 ± 25 Poises (25°C)
- **Color**.....White, as in the catalog and others
- **Finishing**.....Texturized, elastic of medium relief slightly satiny
- **Dry-to-touch**..... ± 1 hour
- **Depth drying**.....± 24 hours
- **Tenor in CIT/MIT**.....<15 ppm
- **VOC (volatile organic compound)**....<sup>a)</sup> EU limit value set for this product subcat. (A/c) 40 g/l (2010). This product contains a maximum of 15 g/l VOC.

### RECOMMENDED USE:

Thanks to its features of impermeability, elasticity and resistance to bad weather, it is recommended for exterior walls coating when it is pretended to associate a decorative finish to the possibility of disguising imperfections and masking cracks on exterior walls.

### SURFACE PREPARATION:

The surface has to be dry, hard, free of dust, grease, dirt, badly adhered sands or exfoliating paints. Concerning concrete or plaster, and to obtain a better finish, to brush properly the surface and to apply a coat as preparation of “TEXTURFLEX” diluted with water (thin stretched film). On whitewashed surfaces, after a good brushing, to apply a coat of “SEALER PLIONEUCE” as a fixative, and wait 24 hours before the application of “TEXTURFLEX”. Concerning repainting, a good brushing of the wall is advised, in order to eliminate old painting remains or to exfoliate. If the surface presents damaged or even “grinded” areas, to apply one coat of “IMPERNEUCE”.

- APPLICATION:** Before to use homogenize well the product.  
The application is to be realized with a honeycomb roller or a brush, in a single coat and without dilution. In the roller application the texturized finishing should be made from the bottom to the top.  
We recommend as insulation coat:
- One coat of “PLIONEUCE PRIMER” – No dilution, whenever the new plaster presents alkalinity or saltpeter signs, or with repainting as promoter of adhesion and protection
  - One coat of “HYDRONEUCE PRIMER” – No dilution.
  - One coat of “MULTINEUCE – Water Based Acrylic Multi-Use Primer” – No dilution
- DILUTION:** With water, if necessary, in quite small quantities.
- COVERAGE:** On average 1,2 to 1,5 m<sup>2</sup>/liter, depending on the plaster absorption.  
For the ‘thin stretched film’ the coverage is of ± 4 m<sup>2</sup>/Liter e per coat.
- CLEAN-UP:** With water right after the application..
- WARNING:** This product is not irritant nor presents any risks of sensitization in a contact with skin. In spite of presenting no risks for health, it is advised to keep out of reach of children.  
For further information, the reading of our product **Safety Data Sheet** is essential.
- RECOMMENDATIONS:** Do not apply with rainy weather, nor with temperatures inferior to 5 °C.  
Concerning applications on walls exposed to the sun and naturally warms, we recommended a previous humidification (wet with water) on them, in order to avoid a too quick drying of “TEXTURFLEX” and defects that can appear.
- STORAGE AND PACKAGING:** Packages should be kept properly closed, in good environmental conditions of temperature and humidity, and spend the product on the chronological order of supply.  
Use it, with preference, up to 2 years after its manufactured date, but it can also be used after this date, as long as a good homogenization of the product can be verified.  
It is supplied in packages of 5 and 15 liters

Note a) The value of the VOC previously mentioned concerns ready-to-use products, according to the technical specifications that we recommend. We do not take any responsibility for other mixtures made to the product. We draw special attention to all our agents for the responsibility that they take by not respecting what the Directive 2004/42/CE establishes.